1. GLASS BEADS

Roundness for glass spheres must have a minimum of 80% true spheres in accordance with AASHTO M247.